

Extrudr

Portfolio coverage, product-level engineering context and comparative public manufacturer positioning.



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6 WORKFLOW-RELIABILITY - Bug Fixes and Workflow Reliability
2026-08-25 19:04:28

Public-data contract: portfolio statistics and positions use only explicitly allowlisted MaterialIDs and existing Verified Material Summary scores. No measurement or score is recalculated.

Public materials
13

Product lines
2

Material types
6

With results
13

Complete profiles
0

Average overall
47,2/100

Public global rank
12 of 25

Benchmark manufacturers
25

Manufacturer overview and public global position


Materials	Product lines	Types	With results	Complete	Average overall	Global rank	Portfolio leader	Strongest axis	With MSRP	With video
13	2	6	13	0	47,2/100	12 of 25	Extrudr DuraPro Neon Green PC/PBT Green	consistency	13	4

Manufacturer website: [Open manufacturer website](#)


Category position by base material

Base material	Public manufacturer position	Average overall	Scored products
ABS	8 of 9	41,5/100	2
ASA	5 of 8	44/100	4
PA12	3 of 6	45/100	2
PA6	1 of 3	56,5/100	2
PC/PBT	1 of 1	54,5/100	2
PLA	15 of 17	42/100	1

Overall leaders



Consistency leaders



Product-level engineering context

MaterialID	Material	Product line	Type	Reinforcement	Coverage	Engineering axes	Overall	Tensile	Impact	Stiffness	Consistency	Layer adhesion	Strongest axis	MSRP USD/kg	Product	Video
MAT0005	Extrudr DuraPro ABS Blue	DuraPro	ABS		Complete	6/5	44/100	16/100	47/100	76/100	71/100	12/100	stiffness	\$21.12	Product page	n/a
MAT0002	Extrudr DuraPro ABS CF Black	DuraPro	ABS	CF	Complete	6/5	39/100	5/100	13/100	93/100	80/100	2/100	stiffness	\$42.27	Product page	n/a
MAT0008	Extrudr DuraPro ASA CF Black	DuraPro	ASA	CF	Complete	6/5	36/100	15/100	14/100	65/100	69/100	16/100	consistency	\$21.97	Product page	n/a
MAT0016	Extrudr DuraPro ASA Red	DuraPro	ASA		Complete	6/5	48/100	19/100	50/100	68/100	80/100	21/100	consistency	\$21.97	Product page	n/a
MAT0014	Extrudr DuraPro Emerald Green ASA Green	DuraPro	ASA		Complete	6/5	51/100	21/100	49/100	67/100	84/100	35/100	consistency	\$21.97	Product page	Video review
MAT0011	Extrudr DuraPro Neon Green ASA GF Green	DuraPro	ASA	GF	Complete	6/5	41/100	15/100	20/100	73/100	76/100	22/100	consistency	\$42.27	Product page	Video review

MaterialID	Material	Product line	Type	Reinforcement	Coverage	Engineering axes	Overall	Tensile	Impact	Stiffness	Consistency	Layer adhesion	Strongest axis	MSRP USD/kg	Product	Video
MAT0196	Extrudr DuraPro Black PA12 CF Black	DuraPro	PA12	CF	Complete	6/5	40/100	28/100	44/100	37/100	74/100	16/100	consistency	\$76.06	Product page	n/a
MAT0020	Extrudr DuraPro PA12 Black	DuraPro	PA12		Complete	6/5	50/100	34/100	50/100	37/100	83/100	43/100	consistency	\$49.80	Product page	n/a
MAT0023	Extrudr DuraPro PA6 CF Black	DuraPro	PA6	CF	Complete	6/5	54/100	52/100	27/100	75/100	71/100	46/100	stiffness	\$39.63	Product page	n/a
MAT0025	Extrudr DuraPro PA6 GF Black	DuraPro	PA6	GF	Complete	6/5	59/100	47/100	48/100	80/100	77/100	44/100	stiffness	\$39.63	Product page	n/a
MAT0031	Extrudr DuraPro Neon Green PC/PBT Green	DuraPro	PC/PBT		Complete	6/5	61/100	33/100	70/100	66/100	92/100	43/100	consistency	\$45.64	Product page	Video review
MAT0030	Extrudr DuraPro PC/PBT CF Black	DuraPro	PC/PBT	CF	Complete	6/5	48/100	23/100	39/100	85/100	77/100	18/100	stiffness	\$54.34	Product page	Video review
MAT0115	Extrudr BioFusion Blue Fire PLA Blue	BioFusion	PLA		Complete	6/5	42/100	21/100	25/100	84/100	77/100	4/100	stiffness	\$19.80	Product page	n/a

Results are comparative 3DPIceland measurements and do not replace manufacturer datasheets or accredited laboratory testing.

[Testing methodology](#) · [Engineering methodology whitepaper](#) · [Download PDF](#)

Stable public path: reports/manufacturers/extrudr/