

Prusa3D Prusament Jet Black PETG V0 Black

Material Engineering Report
MaterialID MAT0048

3DPiceland Engineering Platform

3DPiceland Labs

Generated with 3DPiceland Engineering Platform v60.0.6

WORKFLOW-RELIABILITY - Bug Fixes and Workflow Reliability

Generated 2026-08-25 19:02:26

Public-data contract: This static report contains only allowlisted material identity, public links, canonical MSRP and existing Verified Material Summary / governed score outputs. It excludes raw specimen rows and non-public operational data.

TEST COVERAGE

Complete

ENGINEERING AXES

6/6

PUBLIC MSRP

\$55.60 USD/kg

Material identity


MaterialID	MAT0048
Material	Prusa3D Prusament Jet Black PETG V0 Black
Manufacturer	Prusa3D
Product line	Prusament
Base material	PETG
Category	Standard
Variant / finish	V0
Reinforcement	—
Color	Black

Governed engineering profile


Overall	44/100
Tensile	26/100

Impact	10/100
Stiffness	82/100
Consistency	83/100
Layer adhesion	19/100
Thermal	35/100
Best available axis	consistency

Engineering score profile



Engineering radar



Fixture thermal result

70 °C · score 35/100 · method 3dp-thermal-deflection-fixture-v1

Nearby BlueDOT probe-indicated fixture temperature from a non-standard comparative 3DPIceland method; not ASTM D648, ISO 75, specimen temperature, certified HDT or a manufacturer limit.

Material and manufacturer context

Metric	Selected material	Material average	Manufacturer average
Overall	44/100	42/100	49/100
Tensile	26/100	28/100	31/100
Impact	10/100	16/100	21/100
Stiffness	82/100	60/100	84/100
Consistency	83/100	74/100	79/100
Layer adhesion	19/100	31/100	32/100
Thermal	35/100	—	—

Verified measurement results

Existing Verified Material Summary outputs. The public renderer does not read raw specimen rows or recalculate these values.

Measurement	Average	Std. deviation	CV	Samples	Confidence
Tensile upright	6.598 MPa	1.887 MPa	28.6%	10	10/10
Tensile flat	34.668 MPa	3.208 MPa	9.3%	10	10/10
Impact upright	106.741 kJ/m ²	19.295 kJ/m ²	18.1%	10	10/10
Impact flat	86.366 kJ/m ²	10.595 kJ/m ²	12.3%	10	10/10
Stiffness modulus	2460.163 MPa	—	—	—	—
Stiffness deflection	2.206 mm	—	—	—	—

Measurement provenance

Canonical per-module measured dates from SQLite, shown in unambiguous ISO format. Missing dates are not inferred.

Module	Measured date
Tensile	Not recorded
Impact	Not recorded
Stiffness	Not recorded
Thermal	Not recorded

Engineering interpretation

Summary: Prusa3D Prusament Jet Black PETG V0 Black has a specialized or limited engineering profile. It is above its material-family average by 1,7 points and below its manufacturer average by 5,5 points. Its strongest measured axis is Consistency, while the weakest axis is Impact.

Data-driven review: Prusa3D Prusament Jet Black PETG V0 Black is best understood as a repeatable material for cosmetic, concept and low-load prototype work. Compared with the current verified dataset, it ranks better than 31% overall, is roughly aligned with the material-family average, and is below the manufacturer average by 5,5 points. Its strongest engineering signal is Consistency, while Impact is the main limitation to consider before using it for demanding applications.

BEST FEATURE

Consistency

MAIN LIMITATION

Impact

DATASET POSITION

Better than 31%
162 / 234

Strengths

- Consistency: 83/100. Repeatability is one of the stronger signals in this material profile.
- Stiffness: 82/100. Stiffness is a relative advantage in this comparison group.

Limitations

- Tensile: 26/100. Avoid using this as the primary choice for tensile-loaded parts.
- Impact: 10/100. Avoid high impact or shock-loaded components without additional validation.
- Layer adhesion: 19/100. Z-axis performance should be treated with caution.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.
- Stiffness is useful for shape stability, but impact tolerance is a separate limitation.
- The report should be read as a suitability warning rather than a general-purpose recommendation.

Recommended applications

- Rigid brackets, fixtures and shape-stable prototypes
- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications
- Avoid high impact components

Metric rankings and percentiles

Metric	Score	Rank	Percentile
Overall	44/100	162 / 234	Better than 31%
Tensile	26/100	144 / 226	Better than 37%
Impact	10/100	216 / 226	Better than 5%
Stiffness	82/100	108 / 223	Better than 52%
Consistency	83/100	48 / 231	Better than 80%
Layer adhesion	19/100	139 / 226	Better than 39%
Thermal	35/100	65 / 209	Better than 69%

Decision guidance

- Use this material mainly for low-load, visual or experimental parts.
- Review the listed alternatives if the application needs stronger overall performance.
- Do not choose it as a tensile-strength benchmark material.
- Avoid selecting it for impact-focused testing or shock-loaded designs.

Better alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0236	Yasin Standard Black PETG CF Black	Yasin	50/100	30/100	20/100
MAT0198	Siraya Tech Fiberheart Black PETG Pro CF Black	Siraya Tech	49/100	33/100	19/100
MAT0060	ColorFabb XT PETG Pink	ColorFabb	48/100	—	—

Peer context

Highest-scoring same-base-material peers from the current governed dataset. This context is descriptive and is not recalculated by the public renderer.

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0236	Yasin Standard Black PETG CF Black	Yasin	50/100	30/100	20/100

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0198	Siraya Tech Fiberheart Black PETG Pro CF Black	Siraya Tech	49/100	33/100	19/100
MAT0060	ColorFabb XT PETG Pink	ColorFabb	48/100	—	—
MAT0062	IC3D Standard PETG Green-Yellow	IC3D	48/100	26/100	—
MAT0165	Winkle Standard Ash Gray PETG Gray	Winkle	46/100	30/100	14/100
MAT0225	Spectrum Premium Iceland Blue PETG Blue	Spectrum	46/100	33/100	17/100
MAT0063	IC3D Standard PETG Yellow	IC3D	46/100	26/100	—
MAT0235	Yasin Standard Black PETG GF Black	Yasin	45/100	27/100	21/100

Public links

[Manufacturer website](#) [Video review](#) [Download PDF](#)

Methodology and limitations

Results are comparative 3DPIceland measurements from home-built test equipment. Thermal is a nearby BlueDOT probe-indicated fixture temperature, not ASTM D648, ISO 75 or specimen temperature. Missing evidence remains n/a. Scores and test results are not recalculated by this publishing layer and do not replace certified manufacturer datasheets or accredited laboratory testing.

- [Testing methodology](#)
- [Engineering methodology whitepaper](#)