

Prima Creator PrimaSelect Warm Gray PLA Matte Gray

Material Engineering Report
MaterialID MAT0072

3DP Iceland Engineering Platform
3DP Iceland Labs
Generated with 3DP Iceland Engineering Platform
v60.0.6 WORKFLOW-RELIABILITY - Bug Fixes and
Workflow Reliability
Generated 2026-08-25 19:02:26

Public-data contract: This static report contains only allowlisted material identity, public links, canonical MSRP and existing Verified Material Summary / governed score outputs. It excludes raw specimen rows and non-public operational data.

TEST COVERAGE

Complete

ENGINEERING AXES

6/6

PUBLIC MSRP

\$20.78 USD/kg

Material identity

MaterialID	MAT0072
Material	Prima Creator PrimaSelect Warm Gray PLA Matte Gray
Manufacturer	Prima Creator
Product line	PrimaSelect
Base material	PLA
Category	Standard
Variant / finish	Matte
Reinforcement	—
Color	Gray


Governed engineering profile

Overall


44/100

Tensile	18/100
Impact	30/100
Stiffness	82/100
Consistency	78/100
Layer adhesion	10/100
Thermal	27/100
Best available axis	stiffness

Engineering score profile



Engineering radar



Fixture thermal result

54 °C · score 27/100 · method 3dp-thermal-deflection-fixture-v1

Nearby BlueDOT probe-indicated fixture temperature from a non-standard comparative 3DPIceland method; not ASTM D648, ISO 75, specimen temperature, certified HDT or a manufacturer limit.

Material and manufacturer context

Metric	Selected material	Material average	Manufacturer average
Overall	44/100	50/100	47/100
Tensile	18/100	29/100	27/100
Impact	30/100	24/100	33/100
Stiffness	82/100	87/100	76/100
Consistency	78/100	79/100	78/100
Layer adhesion	10/100	30/100	22/100
Thermal	27/100	—	—

Verified measurement results

Existing Verified Material Summary outputs. The public renderer does not read raw specimen rows or recalculate these values.

Measurement	Average	Std. deviation	CV	Samples	Confidence
Tensile upright	2.707 MPa	1.453 MPa	53.7%	5	5/10
Tensile flat	26.44 MPa	4.948 MPa	18.7%	10	10/10
Impact upright	233.413 kJ/m ²	12.325 kJ/m ²	5.3%	10	10/10
Impact flat	369.751 kJ/m ²	16.19 kJ/m ²	4.4%	10	10/10
Stiffness modulus	2460.163 MPa	—	—	—	—
Stiffness deflection	2.206 mm	—	—	—	—

Measurement provenance

Canonical per-module measured dates from SQLite, shown in unambiguous ISO format. Missing dates are not inferred.

Module	Measured date
Tensile	Not recorded
Impact	Not recorded
Stiffness	Not recorded
Thermal	Not recorded

Engineering interpretation

Summary: Prima Creator PrimaSelect Warm Gray PLA Matte Gray has a specialized or limited engineering profile. It is below its material-family average by 6,5 points and below its manufacturer average by 3,7 points. Its strongest measured axis is Stiffness, while the weakest axis is Layer Adhesion.

Data-driven review: Prima Creator PrimaSelect Warm Gray PLA Matte Gray is best understood as a repeatable material for cosmetic, concept and low-load prototype work. Compared with the current verified dataset, it ranks better than 30% overall, is below the material-family average by 6,5 points, and is below the manufacturer average by 3,7 points. Its strongest engineering signal is Stiffness, while Layer Adhesion is the main limitation to consider before using it for demanding applications.

BEST FEATURE

Stiffness

MAIN LIMITATION

Layer Adhesion

DATASET POSITION

Better than 30%
165 / 234

Strengths

- Consistency: 78/100. Repeatability is one of the stronger signals in this material profile.
- Impact: 30/100. Impact behavior is competitive against the material-family context.
- Stiffness: 82/100. Stiffness is a relative advantage in this comparison group.

Limitations

- Tensile: 18/100. Avoid using this as the primary choice for tensile-loaded parts.
- Impact: 30/100. Avoid high impact or shock-loaded components without additional validation.
- Layer adhesion: 10/100. Z-axis performance should be treated with caution.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.
- Stiffness is useful for shape stability, but impact tolerance is a separate limitation.
- The report should be read as a suitability warning rather than a general-purpose recommendation.

Recommended applications

- Rigid brackets, fixtures and shape-stable prototypes
- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications
- Avoid high impact components

Metric rankings and percentiles

Metric	Score	Rank	Percentile
Overall	44/100	165 / 234	Better than 30%
Tensile	18/100	196 / 226	Better than 14%
Impact	30/100	63 / 226	Better than 73%
Stiffness	82/100	108 / 223	Better than 52%
Consistency	78/100	119 / 231	Better than 49%
Layer adhesion	10/100	203 / 226	Better than 11%
Thermal	27/100	119 / 209	Better than 44%

Decision guidance

- Use this material mainly for low-load, visual or experimental parts.
- Review the listed alternatives if the application needs stronger overall performance.
- Do not choose it as a tensile-strength benchmark material.
- Avoid selecting it for impact-focused testing or shock-loaded designs.

Better alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0069	ProtoPasta HTPLA Blood of My Enemies PLA Red	ProtoPasta	100/100	—	—
MAT0079	Polymaker PolyLight PLA Pro Black	Polymaker	65/100	35/100	52/100
MAT0109	Polymaker PolyMax PLA Black	Polymaker	64/100	32/100	62/100

Peer context

Highest-scoring same-base-material peers from the current governed dataset. This context is descriptive and is not recalculated by the public renderer.

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0069	ProtoPasta HTPLA Blood of My Enemies PLA Red	ProtoPasta	100/100	—	—

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0079	Polymaker PolyLight PLA Pro Black	Polymaker	65/100	35/100	52/100
MAT0109	Polymaker PolyMax PLA Black	Polymaker	64/100	32/100	62/100
MAT0080	Polymaker PolySonic PLA Pro Blue	Polymaker	64/100	30/100	58/100
MAT0076	BambuLab Tough+ PLA Tough+ Black	BambuLab	63/100	26/100	59/100
MAT0108	Polymaker PolyLight PLA Black	Polymaker	61/100	33/100	14/100
MAT0074	Winkle Matte PLA Matte Red	Winkle	60/100	34/100	—
MAT0122	Add:North Enhanced PLA Clear	Add:North	59/100	40/100	10/100

Public links

[Manufacturer website](#) [Download PDF](#)

Methodology and limitations

Results are comparative 3DPrinted measurements from home-built test equipment. Thermal is a nearby BlueDOT probe-indicated fixture temperature, not ASTM D648, ISO 75 or specimen temperature. Missing evidence remains n/a. Scores and test results are not recalculated by this publishing layer and do not replace certified manufacturer datasheets or accredited laboratory testing.

- [Testing methodology](#).
- [Engineering methodology whitepaper](#)