

Yasin Standard Black PA12 CF Black

Material Engineering Report
MaterialID MAT0239

3DPiceland Engineering Platform
3DPiceland Labs

Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow Reliability
Generated 2026-08-25 19:02:26

Public-data contract: This static report contains only allowlisted material identity, public links, canonical MSRP and existing Verified Material Summary / governed score outputs. It excludes raw specimen rows and non-public operational data.

TEST COVERAGE

Complete

ENGINEERING AXES

6/6

PUBLIC MSRP

\$64.48 USD/kg

Material identity

MaterialID	MAT0239
Material	Yasin Standard Black PA12 CF Black
Manufacturer	Yasin
Product line	Standard
Base material	PA12
Category	Engineering
Variant / finish	—
Reinforcement	CF
Color	Black

Governed engineering profile


Overall	41/100
Tensile	33/100

Impact	25/100
Stiffness	64/100
Consistency	78/100
Layer adhesion	7/100
Thermal	53/100
Best available axis	consistency

Engineering score profile



Engineering radar



Fixture thermal result

105 °C · score 53/100 · method 3dp-thermal-deflection-fixture-v1
Nearby BlueDOT probe-indicated fixture temperature from a non-standard comparative 3DPIceland method; not ASTM D648, ISO 75, specimen temperature, certified HDT or a manufacturer limit.

Material and manufacturer context

Metric	Selected material	Material average	Manufacturer average
Overall	41/100	45/100	43/100
Tensile	33/100	32/100	24/100
Impact	25/100	40/100	25/100
Stiffness	64/100	54/100	75/100
Consistency	78/100	75/100	73/100
Layer adhesion	7/100	21/100	19/100
Thermal	53/100	—	—

Verified measurement results

Existing Verified Material Summary outputs. The public renderer does not read raw specimen rows or recalculate these values.

Measurement	Average	Std. deviation	CV	Samples	Confidence
Tensile upright	3.281 MPa	1.191 MPa	36.3%	9	9/10
Tensile flat	49.726 MPa	5.752 MPa	11.6%	10	10/10
Impact upright	139.161 kJ/m ²	42.229 kJ/m ²	30.3%	10	10/10
Impact flat	358.636 kJ/m ²	26.833 kJ/m ²	7.5%	10	10/10
Stiffness modulus	1922.002 MPa	—	—	—	—
Stiffness deflection	2.823 mm	—	—	—	—

Measurement provenance

Canonical per-module measured dates from SQLite, shown in unambiguous ISO format. Missing dates are not inferred.

Module	Measured date
Tensile	2026-08-19
Impact	2026-08-20
Stiffness	2026-08-19
Thermal	2026-08-20

Engineering interpretation

Summary: Yasin Standard Black PA12 CF Black has a specialized or limited engineering profile. It is below its material-family average by 3,1 points and below its manufacturer average by 1,6 points. Its strongest measured axis is Consistency, while the weakest axis is Layer Adhesion.

Data-driven review: Yasin Standard Black PA12 CF Black is best understood as a repeatable material for cosmetic, concept and low-load prototype work. Compared with the current verified dataset, it ranks better than 19% overall, is below the material-family average by 3,1 points, and is roughly aligned with the manufacturer average. Its strongest engineering signal is Consistency, while Layer Adhesion is the main limitation to consider before using it for demanding applications.

BEST FEATURE

Consistency

MAIN LIMITATION

Layer Adhesion

DATASET POSITION

Better than 19%
190 / 234

Strengths

- Consistency: 78/100. Repeatability is one of the stronger signals in this material profile.
- Stiffness: 64/100. Stiffness is a relative advantage in this comparison group.

Limitations

- Tensile: 33/100. Avoid using this as the primary choice for tensile-loaded parts.
- Impact: 25/100. Avoid high impact or shock-loaded components without additional validation.
- Layer adhesion: 7/100. Z-axis performance should be treated with caution.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.
- The report should be read as a suitability warning rather than a general-purpose recommendation.

Recommended applications

- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications
- Avoid high impact components

Metric rankings and percentiles

Metric	Score	Rank	Percentile
Overall	41/100	190 / 234	Better than 19%

Metric	Score	Rank	Percentile
Tensile	33/100	69 / 226	Better than 70%
Impact	25/100	90 / 226	Better than 61%
Stiffness	64/100	173 / 223	Better than 23%
Consistency	78/100	111 / 231	Better than 52%
Layer adhesion	7/100	224 / 226	Better than 1%
Thermal	53/100	14 / 209	Better than 94%

Decision guidance

- Use this material mainly for low-load, visual or experimental parts.
- Review the listed alternatives if the application needs stronger overall performance.
- Do not choose it as a tensile-strength benchmark material.
- Avoid selecting it for impact-focused testing or shock-loaded designs.

Better alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0214	Eryone Standard Black PA12 CF Black	Eryone	53/100	43/100	46/100
MAT0167	BambuLab Basic PA12 PAHT CF Black	BambuLab	51/100	39/100	41/100
MAT0020	Extrudr DuraPro PA12 Black	Extrudr	50/100	34/100	50/100

Peer context

Highest-scoring same-base-material peers from the current governed dataset. This context is descriptive and is not recalculated by the public renderer.

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0214	Eryone Standard Black PA12 CF Black	Eryone	53/100	43/100	46/100
MAT0167	BambuLab Basic PA12 PAHT CF Black	BambuLab	51/100	39/100	41/100
MAT0020	Extrudr DuraPro PA12 Black	Extrudr	50/100	34/100	50/100

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0209	Eryone Standard Black PA12 GF Black	Eryone	49/100	33/100	67/100
MAT0022	Fillamentum FX256 PA12 Clear	Fillamentum	45/100	28/100	47/100
MAT0019	MatterHackers NylonX PA12 CF Black	MatterHackers	42/100	32/100	22/100
MAT0196	Extrudr DuraPro Black PA12 CF Black	Extrudr	40/100	28/100	44/100
MAT0021	Yasin Standard Black PA12 Black	Yasin	31/100	22/100	13/100

Public links

[Manufacturer website](#) [Download PDF](#)

Methodology and limitations

Results are comparative 3DPlceland measurements from home-built test equipment. Thermal is a nearby BlueDOT probe-indicated fixture temperature, not ASTM D648, ISO 75 or specimen temperature. Missing evidence remains n/a. Scores and test results are not recalculated by this publishing layer and do not replace certified manufacturer datasheets or accredited laboratory testing.

- [Testing methodology](#)
- [Engineering methodology whitepaper](#)