

Public printing recommendation

Extrudr DuraPro Emerald Green ASA Green

MaterialID MAT0014



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:05:46

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.

Overall
51/100

Engineering axes
6/5

Public rank
72 / 234

MSRP USD/kg
21.97

Engineering profile



Recommended applications

- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications

Measured strengths

- Layer adhesion: 35/100. Z-axis bonding is better than the material-family context.
- Consistency: 84/100. Repeatability is one of the stronger signals in this material profile.
- Impact: 49/100. Impact behavior is competitive against the material-family context.

Limitations

- Tensile: 21/100. Avoid using this as the primary choice for tensile-loaded parts.
- Layer adhesion: 35/100. Z-axis performance should be treated with caution.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	250	260	270	°C
Bed temperature	110	110	110	°C
Print speed	55	165	165	mm/s
Cooling	20	20	25	%

Guidance	Value	Unit
Cooling guidance	Low	
Drying temperature	85	°C
Drying time	6	hours
Enclosure	Required	
Printer / G-code reference	PrusaCoreOneL	
Slicer profile reference	Prusament ASA	

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.
- Engineering/high-temperature family: confirm enclosure, ventilation, warping control and material-specific drying requirements.
- Layer-adhesion evidence is weak; avoid critical Z-axis loading without additional validation.

Decision guidance

- Use this material for moderate requirements after checking the weakest axis.
- Do not choose it as a tensile-strength benchmark material.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.					

[Testing methodology](#) · [Download PDF](#)

reports/printing-recommendations/MAT0014/