

Public printing recommendation

Yasin Standard Black PA6 GF Black

MaterialID MAT0026



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:05:46

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.


Overall
51/100

Engineering axes
6/5

Public rank
78 / 234

MSRP USD/kg
30.56

Engineering profile



Recommended applications

- Rigid brackets, fixtures and shape-stable prototypes
- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high impact components

Measured strengths

- Consistency: 76/100. Repeatability is one of the stronger signals in this material profile.
- Stiffness: 99/100. Stiffness is a relative advantage in this comparison group.

Limitations

- Impact: 21/100. Avoid high impact or shock-loaded components without additional validation.
- Layer adhesion: 13/100. Z-axis performance should be treated with caution.

Engineering trade-offs

- Stiffness is useful for shape stability, but impact tolerance is a separate limitation.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	280	280	295	°C
Bed temperature	105	110	110	°C
Print speed	11	65	65	mm/s
Cooling	10	10	15	%

Guidance	Value	Unit
Cooling guidance	Low	
Drying temperature	100	°C
Drying time	12	hours
Enclosure	Required	
Printer / G-code reference	PrusaCoreOneL	
Slicer profile reference	Yasin PA6	

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.
- Reinforced filament: confirm an abrasion-resistant nozzle and manufacturer drying/storage requirements.
- Engineering/high-temperature family: confirm enclosure, ventilation, warping control and material-specific drying requirements.
- Layer-adhesion evidence is weak; avoid critical Z-axis loading without additional validation.

Decision guidance

- Use this material for moderate requirements after checking the weakest axis.
- Review the listed alternatives if the application needs stronger overall performance.
- Avoid selecting it for impact-focused testing or shock-loaded designs.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0210	Eryone Standard Black PA6 GF Black	Eryone	72/100	—	40/100
MAT0025	Extrudr DuraPro PA6 GF Black	Extrudr	59/100	47/100	48/100
MAT0023	Extrudr DuraPro PA6 CF Black	Extrudr	54/100	52/100	27/100

Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.

[Testing methodology](#) · [Download PDF](#)

reports/printing-recommendations/MAT0026/