

Public printing recommendation

3D Fuel PCTG Cobalt
Blue PCTG Pro Blue

MaterialID MAT0041



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:05:46

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.

Overall
44/100

Engineering axes
6/5

Public rank
154 / 234

MSRP USD/kg
29.95

Engineering profile



Recommended applications

- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications
- Avoid high impact components

Measured strengths

- Layer adhesion: 43/100. Z-axis bonding is better than the material-family context.
- Consistency: 78/100. Repeatability is one of the stronger signals in this material profile.
- Tensile: 34/100. Tensile behavior is competitive against the material-family context.

Limitations

- Tensile: 34/100. Avoid using this as the primary choice for tensile-loaded parts.
- Impact: 17/100. Avoid high impact or shock-loaded components without additional validation.
- Stiffness: 50/100. Expect less shape stability than the stronger materials in the same family.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.
- The report should be read as a suitability warning rather than a general-purpose recommendation.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	250	260	260	°C
Bed temperature	80	80	80	°C
Print speed	55	110	110	mm/s
Cooling	10	40	40	%
Guidance	Value		Unit	
Cooling guidance	Low			
Drying temperature	65		°C	
Drying time	3		hours	
Enclosure	Not required			
Printer / G-code reference	PrusaCoreOneL			
Slicer profile reference	3D Fuel PCTG			

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.
- Engineering/high-temperature family: confirm enclosure, ventilation, warping control and material-specific drying requirements.

Decision guidance

- Use this material mainly for low-load, visual or experimental parts.
- Review the listed alternatives if the application needs stronger overall performance.
- Do not choose it as a tensile-strength benchmark material.
- Avoid selecting it for impact-focused testing or shock-loaded designs.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0039	3D Fuel PCTG PCTG Pro CF Black	3D Fuel	48/100	27/100	26/100

Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.

[Testing methodology](#) · [Download PDF](#)

reports/printing-recommendations/MAT0041/