

IC3D Standard PETG Green-Yellow

MaterialID MAT0062



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:05:46

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.

Overall 48/100	Engineering axes 3/5	Public rank 107 / 234	MSRP USD/kg 39.00
-------------------	-------------------------	--------------------------	----------------------

Engineering profile

Overall		48/100
Tensile		26/100
Impact		—
Stiffness		—
Consistency		72/100
Layer adhesion		46/100

Recommended applications

- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications
- Avoid high impact components

Measured strengths

- Layer adhesion: 46/100. Z-axis bonding is better than the material-family context.
- Consistency: 72/100. Repeatability is one of the stronger signals in this material profile.

Limitations

- Tensile: 26/100. Avoid using this as the primary choice for tensile-loaded parts.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.
- The report should be read as a suitability warning rather than a general-purpose recommendation.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	230	250	260	°C
Bed temperature	75	85	85	°C
Print speed	55	130	130	mm/s
Cooling	30	60	75	%

Guidance	Value	Unit
Cooling guidance	Moderate	
Drying temperature	65	°C
Drying time	6	hours
Enclosure	Not required	
Printer / G-code reference	PrusaCoreOneL	
Slicer profile reference	Prusament PETG	

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.

Decision guidance

- Use this material mainly for low-load, visual or experimental parts.
- Do not choose it as a tensile-strength benchmark material.

- Avoid selecting it for impact-focused testing or shock-loaded designs.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.					

[Testing methodology](#) · [Download PDF](#)

reports/printing-recommendations/MAT0062/