

Public printing recommendation

Polymaker PolyLight PLA Pro Black

MaterialID MAT0079



3DP Iceland Labs
Generated with 3DP Iceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:05:46

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.

Overall
65/100

Engineering axes
6/5

Public rank
3 / 234

MSRP USD/kg
32.13

Engineering profile



Recommended applications

- Rigid brackets, fixtures and shape-stable prototypes
- Parts where Z-axis bonding is important
- Repeatable print jobs and production-style batches

Measured strengths

- Layer adhesion: 71/100. Z-axis bonding is better than the material-family context.
- Consistency: 84/100. Repeatability is one of the stronger signals in this material profile.
- Impact: 52/100. Impact behavior is competitive against the material-family context.
- Tensile: 35/100. Tensile behavior is competitive against the material-family context.

Limitations

- Tensile: 35/100. Avoid using this as the primary choice for tensile-loaded parts.

Engineering trade-offs

- Good repeatability does not compensate for low tensile capability in load-bearing designs.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	195	230	230	°C
Bed temperature	60	60	70	°C
Print speed	55	165	165	mm/s
Cooling	20	80	85	%
Guidance	Value			Unit
Cooling guidance	High			
Drying temperature	50			°C
Drying time	5			hours
Enclosure	Not required			
Printer / G-code reference	PrusaCoreOneL			
Slicer profile reference	Prusament PLA			

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.

Decision guidance

- Use this material for moderate requirements after checking the weakest axis.
- Review the listed alternatives if the application needs stronger overall performance.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0069	ProtoPasta HTPLA Blood of My Enemies PLA Red	ProtoPasta	100/100	—	—

Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.

[Testing methodology](#) · [Download PDF](#)

reports/printing-recommendations/MAT0079/