

BambuLab Standard Oxide Green Metallic PLA Metal Green

MaterialID MAT0174



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:05:46

Guidance boundary: values below are shared base-material guidance resolved only through the canonical BaseMaterialId link. They are not manufacturer-, spool- or printer-specific validated settings. Missing fields remain Not recorded.

Overall 50/100	Engineering axes 6/5	Public rank 80 / 234	MSRP USD/kg 39.92
-------------------	-------------------------	-------------------------	----------------------

Engineering profile



Recommended applications

- Repeatable print jobs and production-style batches
- Cosmetic parts, concept models or low-load prototypes
- Avoid high tensile load applications

Measured strengths

- Consistency: 84/100. Repeatability is one of the stronger signals in this material profile.
- Impact: 49/100. Impact behavior is competitive against the material-family context.

Limitations

Engineering trade-offs

- Tensile: 26/100. Avoid using this as the primary choice for tensile-loaded parts.
 - Stiffness: 67/100. Expect less shape stability than the stronger materials in the same family.
 - Layer adhesion: 26/100. Z-axis performance should be treated with caution.
- Good repeatability does not compensate for low tensile capability in load-bearing designs.

Base-material printing guidance

Guidance	Minimum	Recommended	Maximum	Unit
Nozzle temperature	195	230	230	°C
Bed temperature	60	60	70	°C
Print speed	55	165	165	mm/s
Cooling	20	80	85	%

Guidance	Value	Unit
Cooling guidance	High	
Drying temperature	50	°C
Drying time	5	hours
Enclosure	Not required	
Printer / G-code reference	PrusaCoreOneL	
Slicer profile reference	Prusament PLA	

Print workflow checks

- Confirm nozzle temperature, bed temperature, speed, cooling and drying requirements from the manufacturer profile or spool label.
- Print a small validation part before committing to a long, costly or safety-relevant print.
- Orient the part so the governing load does not rely on an unverified or weak engineering axis.
- Layer-adhesion evidence is weak; avoid critical Z-axis loading without additional validation.

Decision guidance

- Use this material for moderate requirements after checking the weakest axis.
- Review the listed alternatives if the application needs stronger overall performance.

- Do not choose it as a tensile-strength benchmark material.

Stronger same-family alternatives

MaterialID	Material	Manufacturer	Overall	Tensile	Impact
MAT0069	ProtoPasta HTPLA Blood of My Enemies PLA Red	ProtoPasta	100/100	—	—
MAT0079	Polymaker PolyLight PLA Pro Black	Polymaker	65/100	35/100	52/100
MAT0109	Polymaker PolyMax PLA Black	Polymaker	64/100	32/100	62/100

Confirm exact settings against the manufacturer profile, spool label and actual printer/material combination. Results do not replace application-specific validation.

[Testing methodology](#) · [Download PDF](#)

reports/printing-recommendations/MAT0174/