

# Extrudr BioFusion Blue Fire PLA Blue

MaterialID MAT0115



3DPiceland Labs  
Generated with 3DPiceland Engineering Platform v60.0.6  
WORKFLOW-RELIABILITY - Bug Fixes and Workflow  
Reliability  
2026-08-25 19:04:35

**Traceability boundary:** canonical per-module measured dates are shown below. Session identifier, time of day, operator, printer/slicer profile and environmental conditions are Not recorded and are never inferred.

## Measurement provenance

Canonical SQLite measured dates use ISO format; missing dates remain Not recorded.

| Module    | Measured date |
|-----------|---------------|
| Tensile   | Not recorded  |
| Impact    | Not recorded  |
| Stiffness | Not recorded  |

|                           |                              |                                         |                                   |
|---------------------------|------------------------------|-----------------------------------------|-----------------------------------|
| Status<br><b>Complete</b> | Result modules<br><b>3/3</b> | Specimen/result<br>records<br><b>37</b> | Public details<br><b>Approved</b> |
|---------------------------|------------------------------|-----------------------------------------|-----------------------------------|

## Specimen and result quality

| Module  | Orientation | Average       | Std.<br>dev. | CV     | Specimens | Confidence | Validation |
|---------|-------------|---------------|--------------|--------|-----------|------------|------------|
| Tensile | Upright     | 1,252<br>MPa  | 0,287<br>MPa | 0,229% | 7         | 7/10       | OK         |
| Tensile | Flat        | 33,115<br>MPa | 9,785<br>MPa | 0,295% | 10        | 10/10      | OK         |

| Module    | Orientation      | Average                   | Std. dev.                | CV     | Specimens | Confidence | Validation |
|-----------|------------------|---------------------------|--------------------------|--------|-----------|------------|------------|
| Impact    | Upright          | 155,337 kJ/m <sup>2</sup> | 13,492 kJ/m <sup>2</sup> | 0,087% | 10        | 10/10      | OK         |
| Impact    | Flat             | 354,506 kJ/m <sup>2</sup> | 83,682 kJ/m <sup>2</sup> | 0,236% | 9         | 9/10       | OK         |
| Stiffness | Three-point bend | 2527,565 MPa              | n/a                      | n/a    | 1         | Complete   | OK         |

## Recorded native inputs

| Module    | Input set                 | Recorded values                                                |
|-----------|---------------------------|----------------------------------------------------------------|
| Tensile   | Upright force inputs (N)  | 9, 5, 10, 9, 7, 7, 10, , ,                                     |
| Tensile   | Flat force inputs (N)     | 209, 200, 185, 186, 248, 219, 356, 236, 213, 101               |
| Impact    | Upright needle inputs (%) | 9,00, 9,00, 9,00, 8,00, 8,00, 10,00, 10,00, 10,00, 10,00, 9,00 |
| Impact    | Flat needle inputs (%)    | 22,00, 25,00, 17,00, 31,00, 14,50, 19,00, 17,00, 21,00, 21,00, |
| Stiffness | Revolutions / degrees     | 2 / 10                                                         |

## Approved test notes

## Method and equipment context

Purpose-built tensile, pendulum impact and three-point bend apparatus are used with the governed Settings Manager constants consumed by ResultsService. Results are comparative and do not claim accredited-laboratory equipment.

[Testing methodology](#) · [Engineering methodology whitepaper](#) · [Download PDF](#)

reports/test-sessions/MAT0115/

