

Eryone Standard White ASA GF White

MaterialID MAT0218



3DPiceland Labs
Generated with 3DPiceland Engineering Platform v60.0.6
WORKFLOW-RELIABILITY - Bug Fixes and Workflow
Reliability
2026-08-25 19:04:35

Traceability boundary: canonical per-module measured dates are shown below. Session identifier, time of day, operator, printer/slicer profile and environmental conditions are Not recorded and are never inferred.

Measurement provenance

Canonical SQLite measured dates use ISO format; missing dates remain Not recorded.

Module	Measured date
Tensile	2026-08-01
Impact	2026-08-01
Stiffness	2026-07-31

Status Complete	Result modules 3/3	Specimen/result records 40	Public details Approved
---------------------------	------------------------------	---	-----------------------------------

Specimen and result quality

Module	Orientation	Average	Std. dev.	CV	Specimens	Confidence	Validation
Tensile	Upright	7,629 MPa	9,61 MPa	1,26%	10	10/10	OK
Tensile	Flat	19,414 MPa	8,403 MPa	0,433%	9	9/10	OK

Module	Orientation	Average	Std. dev.	CV	Specimens	Confidence	Validation
Impact	Upright	181,887 kJ/m ²	11,613 kJ/m ²	0,064%	10	10/10	OK
Impact	Flat	368,88 kJ/m ²	23,444 kJ/m ²	0,064%	10	10/10	OK
Stiffness	Three-point bend	2460,163 MPa	n/a	n/a	1	Complete	OK

Recorded native inputs

Module	Input set	Recorded values
Tensile	Upright force inputs (N)	18, 58, 222, 27, 34, 28, 21, 26, 8, 54
Tensile	Flat force inputs (N)	206, 151, 86, 111, 105, 120, 88, 215, 54,
Impact	Upright needle inputs (%)	10,5, 11, 10, 10,5, 11,5, 12, 11, 11, 10, 10
Impact	Flat needle inputs (%)	22, 20, 23, 24, 20, 21, 20, 22,5, 22, 22
Stiffness	Revolutions / degrees	2 / 30

Approved test notes

Method and equipment context

Purpose-built tensile, pendulum impact and three-point bend apparatus are used with the governed Settings Manager constants consumed by ResultsService. Results are comparative and do not claim accredited-laboratory equipment.

[Testing methodology](#) ·
 [Engineering methodology whitepaper](#) ·
 [Download PDF](#)

reports/test-sessions/MAT0218/

